




FREIOTHERM-Powder Coating

PS5205B

Characteristics	■ Powder coating for decorative use on exteriors ■ Application, e.g. in the vehicle construction sector ■ high glossy, smooth ■ Good mechanical resistance and surface hardness ■ Super-durable quality												
System Coating	■ System Liquid Coating For various applications, there are coatings available, whose optical appearance regarding colour, gloss degree and surface is in optimum balance.												
Technical / Physical Data	<table> <tr> <td>■ Binder-Base</td><td>polyester resin</td></tr> <tr> <td>■ Colour</td><td>all common colour shades</td></tr> <tr> <td>■ Gloss value DIN EN ISO 2813</td><td>high glossy >85 geometry 60°</td></tr> <tr> <td>■ Test layer thickness</td><td>100 µm by colour RAL 3002</td></tr> <tr> <td>■ Density calculated</td><td>1,2-1,7 g/cm³ colour-dependent</td></tr> <tr> <td>■ Material usage</td><td>0,15 kg/m² with 100 µm mean test layer thickness</td></tr> </table>	■ Binder-Base	polyester resin	■ Colour	all common colour shades	■ Gloss value DIN EN ISO 2813	high glossy >85 geometry 60°	■ Test layer thickness	100 µm by colour RAL 3002	■ Density calculated	1,2-1,7 g/cm³ colour-dependent	■ Material usage	0,15 kg/m² with 100 µm mean test layer thickness
■ Binder-Base	polyester resin												
■ Colour	all common colour shades												
■ Gloss value DIN EN ISO 2813	high glossy >85 geometry 60°												
■ Test layer thickness	100 µm by colour RAL 3002												
■ Density calculated	1,2-1,7 g/cm³ colour-dependent												
■ Material usage	0,15 kg/m² with 100 µm mean test layer thickness												
Mechanical Test on steel panel ST 1405	<table> <tr> <td>■ Cross-cut-test DIN EN ISO 2409</td><td>Gt 0</td></tr> <tr> <td>■ Erichsen index DIN EN ISO 1520</td><td>>3 mm</td></tr> <tr> <td>■ Impact-Test DIN EN ISO 6272-1</td><td>80 kg cm (front)</td></tr> </table>	■ Cross-cut-test DIN EN ISO 2409	Gt 0	■ Erichsen index DIN EN ISO 1520	>3 mm	■ Impact-Test DIN EN ISO 6272-1	80 kg cm (front)						
■ Cross-cut-test DIN EN ISO 2409	Gt 0												
■ Erichsen index DIN EN ISO 1520	>3 mm												
■ Impact-Test DIN EN ISO 6272-1	80 kg cm (front)												
Resistance Test	■ on blasted steel plate with suitable primer <table> <tr> <td>■ Salt spray test (NSS) DIN EN ISO 9227</td><td>hours Water ingress Wb < 3 mm DIN EN ISO 4628-8</td></tr> <tr> <td>■ Chemical resistance</td><td>Needs to be checked. The temperature and concentration of chemicals have a major influence on the test outcome.</td></tr> </table>	■ Salt spray test (NSS) DIN EN ISO 9227	hours Water ingress Wb < 3 mm DIN EN ISO 4628-8	■ Chemical resistance	Needs to be checked. The temperature and concentration of chemicals have a major influence on the test outcome.								
■ Salt spray test (NSS) DIN EN ISO 9227	hours Water ingress Wb < 3 mm DIN EN ISO 4628-8												
■ Chemical resistance	Needs to be checked. The temperature and concentration of chemicals have a major influence on the test outcome.												
Processing and application Dependent on plant and buildings	■ Processing / Loading Corona ■ Pretreatment The substrate must be free of adhesion-impairing substances such as oil, grease, rust, scale, rolling skin, wax and separating agent residue. If requirements are more demanding than this, we recommend appropriate levels of phosphatizing or chromatizing. ■ Touch-up coating: on enquiry ■ Health & Safety at Work guidelines The standard personal safety precautions must be observed when handling painting materials. Detailed information about dangerous goods, safety data and recommendations concerning Health & Safety at Work and environmental protection can be found in the corresponding safety data sheet.												



FREIOTHERM-Powder Coating PS5205B

Curing


Object temperature

Recommended baking temperature 10 min./180 °C

Baking window tested in colour shade 3002

green cross-hatching = baking conditions with good final properties

Objekt Temperatur °C	170	180	190	200	
Object Temperature °C					
Haltezeit Minimum Minuten	20	10	8	6	
Holding time minimum Minutes					
Haltezeit Maximum Minuten	60	45	35	25	
Holding time maximum Minutes					



Resistance to storage

- Approx. 24 month in original packagings at an ambient temperature of 5 to 25 °C. Powder coatings must be stored in a cool and dry place.

The minimum storage stability of each batch is stated on the product label. The material does not necessarily become unusable if stored for longer than this period. However, for quality assurance purposes, an inspection of these materials is essential to ensure that they are still suitable for the intended application.

Specific comments

- Protective screening:** 160 µm

- Compatibility with other powder coatings:** Needs to be checked

Test conditions

All information is based on a standard climate 23/50 DIN EN 23270.

All information is based on our product knowledge and experience. We have no direct influence on the application itself. Please do not hesitate to contact us for further information.

The information provided here contains reference values and does not constitute a specification.