


FREIOTHERM-Hydro-Coating


WO1839H


Characteristics	- Water-thinnable single-layer coating - Application, e.g. in the mechanical engineering and plant construction sector - Good condensation resistance - Can be coated over with powder coatings	
Technical / Physical Data	- Binder-Base: Combination of polyester/amino resin - Colour: All common colour shades - Gloss value DIN EN ISO 2813: mat 25-35 Angle 60° - Viscosity DIN 53211 (formerly): Flow time 23-26 seconds 4 mm viscosity cup - Thinner: demineralised water - pH-Value: 8,7-9,0 - Density calculated: 1,25-1,35 g/ml - Solid Mass calculated: 43-47 % - Solid content in volume calculated: 225-245 ml/kg - Material usage theoretical, without application loss: 325-355 g/m², Layer thickness 80 µm - Reference colour of the specified values: Colour of WO1839HND008	
Substrate	- Steel - Steel - preliminary test required for galvanised substrates - Aluminium	
Pretreatment	The substrate must be free of adhesion-impairing substances such as oil, grease, rust, scale, rolling skin, wax and separating agent residue. Preliminary tests are recommended for assuring the suitability of coating qualities on the substrate. For more stringent requirements, we recommend: for corrosion protection - e.g. phosphating for adhesion - e.g. blasting, pickling, sanding	
Structure recommendation	- Substrate: on iron-phosphated steel plate - Top coat: WO1839HND008 Dry film thickness 30 µm	
Mechanical Test	Cross-cut-test DIN EN ISO 2409: Gt 0	
Processing and application	- Prior to use, stir well or mix components homogeneously (e.g. with fast mixer). To prevent skin formation, over-coat with water. Dry film thickness must not exceed 35 µm - risk of reaction bubbles. - Object temperature: 10-30 °C	

Our technical data sheets are to provide you with advice based on our latest state of knowledge. This guidance does not release you from your own obligation to test our products for their suitability for your intended purposes and applications. The sale of our products is in accordance with our terms of business and delivery.



FREIOTHERM-Hydro-Coating **WO1839H**

	■ Processing conditions Room temperature 18-22 °C Relative humidity 40-60 % ■ High pressure spraying as delivered viscosity Nozzle: 1,5 mm Spray pressure 3-4 bar ■ Electrostatic possible, system-specific ■ Over-coating capability possible with same quality, dry at the earliest after matting ■ Cleaning of equipment Immediately with water - possibly with addition of 5-10 % by weight EFD cleaning agent 400916. Dried-on equipment with org. solvents, e.g. EFD thinner 400424. ■ Health & Safety at Work guidelines The standard personal safety precautions must be observed when handling painting materials. Detailed information about dangerous substances, safety data and recommendations concerning Health & Safety at Work and environmental protection can be found in the corresponding safety data sheet.
Curing	■ Oven drying 30 min./ 140 °C - 15 min./ 160 °C ■ Object temperature green cross-hatching = baking conditions with good final properties 
Resistance to storage	■ Approx. 12 month in original packagings at an ambient temperature of 5 to 25 °C. Protect from frost. Open packages are to be used within a short time. The minimum storage stability of each batch is stated on the product label. The material does not necessarily become unusable if stored for longer than this period. However, for quality assurance purposes, an inspection of these materials is essential to ensure that they are still suitable for the intended application.
Specific comments	■ EFD-info Refer to the EFD information for further technical information. Nr. 111



FREIOTHERM-Hydro-Coating **WO1839H**

■ **Test conditions**

All information is based on a standard climate 23/50 DIN EN 23270.

All information is based on our product knowledge and experience. We have no direct influence on the application itself. Please do not hesitate to contact us for further information.

The information provided here contains reference values and does not constitute a specification.