



FREIOTHERM-ATL-Whiteness

WA4116HRU916

Characteristics	■ Anodic electrocoat paint depositable 1K ■ Application, e.g. in the construction and sanitary sector ■ Subsequent paste filling, partly neutralised														
Technical / Physical Data	<table> <tr> <td>■ Binder-Base</td><td>Acrylic Resin</td></tr> <tr> <td>■ Colour</td><td>traffic white Based on the specified colour template (i.e. RAL)</td></tr> <tr> <td>■ Solid Mass DIN EN ISO 3251</td><td>68-72 %</td></tr> <tr> <td>■ Density calculated</td><td>1,31 g/cm³</td></tr> <tr> <td>■ MEQ-Base-Value DIN EN ISO 15880</td><td>27-33</td></tr> <tr> <td>■ Viscosity</td><td>3000-7000 mPa.s</td></tr> <tr> <td>■ Test layer thickness</td><td>16-24 µm</td></tr> </table>	■ Binder-Base	Acrylic Resin	■ Colour	traffic white Based on the specified colour template (i.e. RAL)	■ Solid Mass DIN EN ISO 3251	68-72 %	■ Density calculated	1,31 g/cm ³	■ MEQ-Base-Value DIN EN ISO 15880	27-33	■ Viscosity	3000-7000 mPa.s	■ Test layer thickness	16-24 µm
■ Binder-Base	Acrylic Resin														
■ Colour	traffic white Based on the specified colour template (i.e. RAL)														
■ Solid Mass DIN EN ISO 3251	68-72 %														
■ Density calculated	1,31 g/cm ³														
■ MEQ-Base-Value DIN EN ISO 15880	27-33														
■ Viscosity	3000-7000 mPa.s														
■ Test layer thickness	16-24 µm														
Processing and application Dependent on plant and buildings	■ Method The procedure is dependant upon various factors and is therefore matched to the application technology to the individual plant. ■ Health & Safety at Work guidelines The standard personal safety precautions must be observed when handling painting materials. Detailed information about dangerous goods, safety data and recommendations concerning Health & Safety at Work and environmental protection can be found in the corresponding safety data sheet.														
Curing	■ Object temperature Recommended baking temperature 20 Min./170 °C green cross-hatching = baking conditions with good final properties														
Resistance to storage	■ Approx. 12 Monate month in original packagings at an ambient temperature of 5 to 25 °C. Protect from frost. Open packages are to be used within a short time. The minimum storage stability of each batch is stated on the product label. The														

Our technical data sheets are to provide you with advice based on our latest state of knowledge. This guidance does not release you from your own obligation to test our products for their suitability for your intended purposes and applications. The sale of our products is in accordance with our terms of business and delivery.

**FREIOTHERM-ATL-Whiteness**
WA4116HRU916

material does not necessarily become unusable if stored for longer than this period. However, for quality assurance purposes, an inspection of these materials is essential to ensure that they are still suitable for the intended application.

Specific comments■ **Test conditions**

All information is based on a standard climate 23/50 DIN EN 23270.

All information is based on our product knowledge and experience. We have no direct influence on the application itself. Please do not hesitate to contact us for further information.

The information provided here contains reference values and does not constitute a specification.