


# EFD-Hydro-Repair-Coating WL1004H

<b>Characteristics</b>	<ul style="list-style-type: none"> <li>Water-thinnable 1C coating</li> <li>Application, e.g. in the mechanical engineering and plant construction sector</li> <li>For touching up minor coating damage after transport and assembly</li> </ul>																						
<b>Technical / Physical Data</b>	<table> <tr> <td>Binder-Base</td><td>Acrylate-styrene copolymer</td></tr> <tr> <td>Colour</td><td>All common colour shades</td></tr> <tr> <td>Gloss value visual</td><td>satin mat</td></tr> <tr> <td>Viscosity</td><td>3000-5000 mPa.s/ Spindle 5 60 revolution/ min.</td></tr> <tr> <td>Thinner</td><td>demineralised water</td></tr> <tr> <td>pH-Value</td><td>8,4-8,7</td></tr> <tr> <td>Density calculated</td><td>1,05-1,25 g/ml</td></tr> <tr> <td>Solid Mass calculated</td><td>34-42 %</td></tr> <tr> <td>Solid content in volume calculated</td><td>275-285 ml/kg</td></tr> <tr> <td>Material usage theoretical, without application loss</td><td>135-145 g/m<sup>2</sup>, Layer thickness 40 µm</td></tr> <tr> <td>Reference colour of the specified values</td><td>Colour of WL1004HT2132</td></tr> </table>	Binder-Base	Acrylate-styrene copolymer	Colour	All common colour shades	Gloss value visual	satin mat	Viscosity	3000-5000 mPa.s/ Spindle 5 60 revolution/ min.	Thinner	demineralised water	pH-Value	8,4-8,7	Density calculated	1,05-1,25 g/ml	Solid Mass calculated	34-42 %	Solid content in volume calculated	275-285 ml/kg	Material usage theoretical, without application loss	135-145 g/m <sup>2</sup> , Layer thickness 40 µm	Reference colour of the specified values	Colour of WL1004HT2132
Binder-Base	Acrylate-styrene copolymer																						
Colour	All common colour shades																						
Gloss value visual	satin mat																						
Viscosity	3000-5000 mPa.s/ Spindle 5 60 revolution/ min.																						
Thinner	demineralised water																						
pH-Value	8,4-8,7																						
Density calculated	1,05-1,25 g/ml																						
Solid Mass calculated	34-42 %																						
Solid content in volume calculated	275-285 ml/kg																						
Material usage theoretical, without application loss	135-145 g/m <sup>2</sup> , Layer thickness 40 µm																						
Reference colour of the specified values	Colour of WL1004HT2132																						
<b>Substrate</b>	<ul style="list-style-type: none"> <li>Primer</li> </ul>																						
<b>Pretreatment</b>	<ul style="list-style-type: none"> <li>The substrate must be free of adhesion-impairing substances such as oil, grease, wax and separating agent residue. Preliminary tests are recommended for assuring the suitability of coating qualities on the substrate.</li> </ul>																						
<b>Structure recommendation</b>	<table> <tr> <td>Substrate</td><td>according to customer requirements</td></tr> <tr> <td>Top coat</td><td>WL1004HT2132 Dry film thickness 40 µm</td></tr> </table>	Substrate	according to customer requirements	Top coat	WL1004HT2132 Dry film thickness 40 µm																		
Substrate	according to customer requirements																						
Top coat	WL1004HT2132 Dry film thickness 40 µm																						
<b>Mechanical Test</b>	<table> <tr> <td>Cross-cut-test DIN EN ISO 2409</td><td>Gt 0</td></tr> </table>	Cross-cut-test DIN EN ISO 2409	Gt 0																				
Cross-cut-test DIN EN ISO 2409	Gt 0																						
<b>Processing and application</b>	<ul style="list-style-type: none"> <li>Prior to use, stir well or mix components homogeneously (e.g. with fast mixer). To prevent skin formation, over-coat with water. Dry film thickness must not exceed 100 µm - risk of reaction bubbles.</li> <li>Object temperature: 10-30 °C</li> <li>Processing conditions: Room temperature 18-22 °C Relative humidity 40-60 %</li> <li>Rolling / painting: as delivered viscosity</li> <li>Cleaning of equipment: Immediately with water - possibly with addition of 5-10 % by weight EFD cleaning agent 400916. Dried-on equipment with org. solvents, e.g. EFD thinner 400424.</li> </ul>																						

Our technical data sheets are to provide you with advice based on our latest state of knowledge. This guidance does not release you from your own obligation to test our products for their suitability for your intended purposes and applications. The sale of our products is in accordance with our terms of business and delivery.



## EFD-Hydro-Repair-Coating WL1004H

	<b>Health &amp; Safety at Work guidelines</b> The standard personal safety precautions must be observed when handling painting materials. Detailed information about dangerous substances, safety data and recommendations concerning Health & Safety at Work and environmental protection can be found in the corresponding safety data sheet.	
<b>Curing</b>	Air drying	at 18-22 °C, 40-60 % relative humidity with air movement
	Dust drying	after 40 min. (degree of drying 1/ DIN EN ISO 9117-5)
	Dry to the touch	after 2 hrs. (degree of drying 4/ DIN EN ISO 9117-5)
	Full drying	after 5 days (pendulum damping/DIN EN ISO 1522)
	Oven drying	possible to 70°C
<b>Resistance to storage</b>	<b>Approx. 12 month in original packagings at an ambient temperature of 5 to 25 °C.</b> Protect from frost. Open packages are to be used within a short time.  The minimum storage stability of each batch is stated on the product label. The material does not necessarily become unusable if stored for longer than this period. However, for quality assurance purposes, an inspection of these materials is essential to ensure that they are still suitable for the intended application.	
<b>Specific comments</b>	<b>EFD-info</b> Refer to the EFD information for further technical information. Nr. 111	
	<b>Test conditions</b> All information is based on a standard climate 23/50 DIN EN 23270. All information is based on our product knowledge and experience. We have no direct influence on the application itself. Please do not hesitate to contact us for further information.  The information provided here contains reference values and does not constitute a specification.	