


FREIOPLAST-Hydro-EdgeProtect WL1525L

Characteristics	<ul style="list-style-type: none"> Water-thinnable single-layer coating Application, e.g. in the construction and sanitary sector Fast initial drying Suitable for derived timber products 																						
Technical / Physical Data	<table> <tr> <td>Binder-Base</td><td>Acrylate-styrene copolymer</td></tr> <tr> <td>Colour</td><td>All common colour shades</td></tr> <tr> <td>Gloss value DIN EN ISO 2813</td><td>mat 45-56 Angle 85°</td></tr> <tr> <td>Viscosity</td><td>500-1000 mPa.s/ Spindle 4 60 revolution/ min.</td></tr> <tr> <td>Thinner</td><td>demineralised water</td></tr> <tr> <td>pH-Value</td><td>8,5-9,1</td></tr> <tr> <td>Density calculated</td><td>0,95-1,05 g/ml</td></tr> <tr> <td>Solid Mass calculated</td><td>16-21 %</td></tr> <tr> <td>Solid content in volume calculated</td><td>125-145 ml/kg</td></tr> <tr> <td>Material usage theoretical, without application loss</td><td>550-600 g/m², Layer thickness 80 µm</td></tr> <tr> <td>Reference colour of the specified values</td><td>Colour of WL1525LH3059</td></tr> </table>	Binder-Base	Acrylate-styrene copolymer	Colour	All common colour shades	Gloss value DIN EN ISO 2813	mat 45-56 Angle 85°	Viscosity	500-1000 mPa.s/ Spindle 4 60 revolution/ min.	Thinner	demineralised water	pH-Value	8,5-9,1	Density calculated	0,95-1,05 g/ml	Solid Mass calculated	16-21 %	Solid content in volume calculated	125-145 ml/kg	Material usage theoretical, without application loss	550-600 g/m², Layer thickness 80 µm	Reference colour of the specified values	Colour of WL1525LH3059
Binder-Base	Acrylate-styrene copolymer																						
Colour	All common colour shades																						
Gloss value DIN EN ISO 2813	mat 45-56 Angle 85°																						
Viscosity	500-1000 mPa.s/ Spindle 4 60 revolution/ min.																						
Thinner	demineralised water																						
pH-Value	8,5-9,1																						
Density calculated	0,95-1,05 g/ml																						
Solid Mass calculated	16-21 %																						
Solid content in volume calculated	125-145 ml/kg																						
Material usage theoretical, without application loss	550-600 g/m², Layer thickness 80 µm																						
Reference colour of the specified values	Colour of WL1525LH3059																						
Substrate	<ul style="list-style-type: none"> Wood 																						
Pretreatment	<ul style="list-style-type: none"> The substrate must be free of adhesion-impairing substances such as oil, grease, wax and separating agent residue. Preliminary tests are recommended for assuring the suitability of coating qualities on the substrate. 																						
Structure recommendation	<table> <tr> <td>Substrate</td><td>Wood</td></tr> <tr> <td>Top coat</td><td>WL1525LH3059 Dry film thickness 60 µm</td></tr> </table>	Substrate	Wood	Top coat	WL1525LH3059 Dry film thickness 60 µm																		
Substrate	Wood																						
Top coat	WL1525LH3059 Dry film thickness 60 µm																						
Mechanical Test	<table> <tr> <td>Cross-cut-test DIN EN ISO 2409</td><td>Gt 0</td></tr> </table>	Cross-cut-test DIN EN ISO 2409	Gt 0																				
Cross-cut-test DIN EN ISO 2409	Gt 0																						
Processing and application	<ul style="list-style-type: none"> Prior to use, stir well or mix components homogeneously (e.g. with fast mixer). To prevent skin formation, over-coat with water. Object temperature 10-30 °C Processing conditions Room temperature 18-25 °C Relative humidity 40-60 % Airless spraying as delivered viscosity Nozzle 11 mm angle 40° Material pressure 140 bar High pressure spraying 40-50 Sec./ 4 mm Viscosity cup (DIN 53211) Nozzle 1,4 mm 																						

Our technical data sheets are to provide you with advice based on our latest state of knowledge. This guidance does not release you from your own obligation to test our products for their suitability for your intended purposes and applications. The sale of our products is in accordance with our terms of business and delivery.



FREIOPLAST-Hydro-EdgeProtect

WL1525L

		Spray pressure 3,5 bar
	■ Over-coating capability	possible with same quality, dry at the earliest after matting
	■ Cleaning of equipment	Immediately with water - possibly with addition of 5-10 % by weight EFD cleaning agent 400916. Dried-on equipment with org. solvents, e.g. EFD thinner 400424.
	■ Health & Safety at Work guidelines	The standard personal safety precautions must be observed when handling painting materials. Detailed information about dangerous substances, safety data and recommendations concerning Health & Safety at Work and environmental protection can be found in the corresponding safety data sheet.
Curing	■ Air drying	at 20 °C, 40-70 % relative humidity with air movement
	■ Dust drying	after 15 min. (degree of drying 1/ DIN EN ISO 9117-5)
	■ Dry to the touch	after 1 hrs. (degree of drying 4/ DIN EN ISO 9117-5)
	■ Full drying	after 17 days (pendulum damping/DIN EN ISO 1522)
	■ Oven drying	possible to 70°C
Resistance to storage	■	Approx. 12 month in original packagings at an ambient temperature of 5 to 25 °C. Protect from frost. Open packages are to be used within a short time.
		The minimum storage stability of each batch is stated on the product label. The material does not necessarily become unusable if stored for longer than this period. However, for quality assurance purposes, an inspection of these materials is essential to ensure that they are still suitable for the intended application.
Specific comments	■ EFD-info	Refer to the EFD information for further technical information. Nr. 111
	■ Test conditions	All information is based on a standard climate 23/50 DIN EN 23270. All information is based on our product knowledge and experience. We have no direct influence on the application itself. Please do not hesitate to contact us for further information.
		The information provided here contains reference values and does not constitute a specification.