



# FREIOTHERM-ATL-Low-Solvent

## WA4806HL1866

<b>Characteristics</b>	<ul style="list-style-type: none"> <li>■ Anodic electrocoat paint depositable 1K</li> <li>■ Application, e.g. in the functional furniture and storage technology sector</li> <li>■ Subsequent paste filling, partly neutralised</li> <li>■ Single coat system</li> </ul>														
<b>Technical / Physical Data</b>	<table> <tr> <td>■ Binder-Base</td><td>Acrylic Resin</td></tr> <tr> <td>■ Colour</td><td>lenzen brown Based on the specified colour template (i.e. RAL)</td></tr> <tr> <td>■ Solid Mass DIN EN ISO 3251</td><td>41-45 %</td></tr> <tr> <td>■ Density calculated</td><td>1,10 g/cm<sup>3</sup></td></tr> <tr> <td>■ MEQ-Base-Value DIN EN ISO 15880</td><td>28-35</td></tr> <tr> <td>■ Viscosity</td><td>1000-5000 mPa.s</td></tr> <tr> <td>■ Test layer thickness</td><td>3-8 µm</td></tr> </table>	■ Binder-Base	Acrylic Resin	■ Colour	lenzen brown Based on the specified colour template (i.e. RAL)	■ Solid Mass DIN EN ISO 3251	41-45 %	■ Density calculated	1,10 g/cm <sup>3</sup>	■ MEQ-Base-Value DIN EN ISO 15880	28-35	■ Viscosity	1000-5000 mPa.s	■ Test layer thickness	3-8 µm
■ Binder-Base	Acrylic Resin														
■ Colour	lenzen brown Based on the specified colour template (i.e. RAL)														
■ Solid Mass DIN EN ISO 3251	41-45 %														
■ Density calculated	1,10 g/cm <sup>3</sup>														
■ MEQ-Base-Value DIN EN ISO 15880	28-35														
■ Viscosity	1000-5000 mPa.s														
■ Test layer thickness	3-8 µm														
<b>Processing and application</b> Dependent on plant and buildings	<ul style="list-style-type: none"> <li>■ <b>Pretreatment</b> The substrate must be free of adhesion-impairing substances such as oil, grease, rust, scale, rolling skin, wax and separating agent residue.</li> <li>■ Gloss value DIN EN ISO 2813</li> <li>■ pH-Value</li> <li>■ Cunductance</li> <li>■ Solid Mass DIN EN ISO 3251</li> <li>■ MEQ-Base-Value DIN EN ISO 15880</li> <li>■ Organic Solvent Content</li> <li>■ Bath Temperature</li> <li>■ Coating Time</li> <li>■ Deposition Voltage</li> <li>■ <b>Health &amp; Safety at Work guidelines</b> The standard personal safety precautions must be observed when handling painting materials. Detailed information about dangerous goods, safety data and recommendations concerning Health &amp; Safety at Work and environmental protection can be found in the corresponding safety data sheet.</li> </ul>														
<b>Resistance to storage</b>	<ul style="list-style-type: none"> <li>■ One Turn-Over per year</li> </ul> <p>Approx. 12 month in original packagings at an ambient temperature of 5 to 25 °C. Protect from frost. Open packages are to be used within a short time.</p> <p>The minimum storage stability of each batch is stated on the product label. The material does not necessarily become unusable if stored for longer than this period.</p>														

**FREIOTHERM-ATL-Low-Solvent**  
**WA4806HL1866**

However, for quality assurance purposes, an inspection of these materials is essential to ensure that they are still suitable for the intended application.

**Specific comments**■ **Test conditions**

All information is based on a standard climate 23/50 DIN EN 23270.

All information is based on our product knowledge and experience. We have no direct influence on the application itself. Please do not hesitate to contact us for further information.

The information provided here contains reference values and does not constitute a specification.