




FREIOTHERM-Hydro-Coating **WO1839V**

Characteristics	<ul style="list-style-type: none"> Water-thinnable single-layer coating Application, e.g. in the mechanical engineering and plant construction sector Good condensation resistance Can be coated over with powder coatings 	
Technical / Physical Data	<ul style="list-style-type: none"> Binder-Base: Combination of polyester/amino resin Colour: All common colour shades Gloss value DIN EN ISO 2813: mat 30-50 Angle 85° Viscosity DIN 53211 (formerly): Flow time 42-45 seconds 4 mm viscosity cup Thinner: demineralised water pH-Value: 8,7-8,9 Density calculated: 1,25-1,35 g/ml Solid Mass calculated: 47-50 % Solid content in volume calculated: 235-245 ml/kg Material usage theoretical, without application loss: 325-340 g/m², Layer thickness 80 µm Reference colour of the specified values: Colour of WO1839VS1501 	
Substrate	<ul style="list-style-type: none"> Steel Steel - preliminary test required for galvanised substrates Aluminium 	
Pretreatment	<ul style="list-style-type: none"> The substrate must be free of adhesion-impairing substances such as oil, grease, rust, scale, rolling skin, wax and separating agent residue. Preliminary tests are recommended for assuring the suitability of coating qualities on the substrate. For more stringent requirements, we recommend: for corrosion protection - e.g. phosphating for adhesion - e.g. blasting, pickling, sanding 	
Structure recommendation	<ul style="list-style-type: none"> Substrate: on iron-phosphated steel plate Top coat: WO1839VS1501 Dry film thickness 30 µm 	
Mechanical Test	<ul style="list-style-type: none"> Cross-cut-test DIN EN ISO 2409: Gt 0 	
Processing and application	<ul style="list-style-type: none"> Prior to use, stir well or mix components homogeneously (e.g. with fast mixer). To prevent skin formation, over-coat with water. Dry film thickness must not exceed 40 µm - risk of reaction bubbles. Object temperature: 10-30 °C 	

Our technical data sheets are to provide you with advice based on our latest state of knowledge. This guidance does not release you from your own obligation to test our products for their suitability for your intended purposes and applications. The sale of our products is in accordance with our terms of business and delivery.



FREIOTHERM-Hydro-Coating WO1839V

	■ Processing conditions	Room temperature 18-22 °C Relative humidity 40-60 %
	■ High pressure spraying	as delivered viscosity Nozzle: 1,5 mm Spray pressure 3-4 bar
	■ Immersing	42-45 Sec/ 4 mm Viscosity cup (DIN 53211)
	■ Pouring	42-45 Sec./ 4 mm Viscosity cup (DIN 53211)
	■ Electrostatic	possible, system-specific
	■ Over-coating capability	possible based on pre-test
	■ Cleaning of equipment	Immediately with water - possibly with addition of 5-10 % by weight EFD cleaning agent 400916. Dried-on equipment with org. solvents, e.g. EFD thinner 400424.
	■ Health & Safety at Work guidelines	The standard personal safety precautions must be observed when handling painting materials. Detailed information about dangerous substances, safety data and recommendations concerning Health & Safety at Work and environmental protection can be found in the corresponding safety data sheet.
Curing	■ Oven drying	30 min./ 140 °C - 15 min./ 160 °C
	■ Object temperature	green cross-hatching = baking conditions with good final properties
Resistance to storage	■ Approx. 12 month in original packagings at an ambient temperature of 5 to 25 °C. Protect from frost. Open packages are to be used within a short time.	
	<p>The minimum storage stability of each batch is stated on the product label. The material does not necessarily become unusable if stored for longer than this period. However, for quality assurance purposes, an inspection of these materials is essential to ensure that they are still suitable for the intended application.</p>	
Specific comments		

Our technical data sheets are to provide you with advice based on our latest state of knowledge. This guidance does not release you from your own obligation to test our products for their suitability for your intended purposes and applications. The sale of our products is in accordance with our terms of business and delivery.



FREIOTHERM-Hydro-Coating **WO1839V**

■ **EFD-info**

Refer to the EFD information for further technical information.
Nr. 111

■ **Test conditions**

All information is based on a standard climate 23/50 DIN EN 23270.
All information is based on our product knowledge and experience. We have no direct influence on the application itself. Please do not hesitate to contact us for further information.

The information provided here contains reference values and does not constitute a specification.