



FREIOTHERM-ATL-Special

WA4900HRU905


Characteristics	■ Anodic electrocoat paint depositable 1K ■ Application, e.g. in the functional furniture and storage technology sector ■ Subsequent paste filling, partly neutralised ■ Single coat system	
Technical / Physical Data	■ Binder-Base Acrylic Resin ■ Colour black Based on the specified colour template (i.e. RAL) ■ Solid Mass DIN EN ISO 3251 63-67 % ■ Density calculated 1,07 g/cm³ ■ MEQ-Base-Value DIN EN ISO 15880 37-44 ■ Viscosity 2500-7500 mPa.s ■ Test layer thickness 20-25 µm	
Mechanical Test	■ on steel, purified alkaline ■ Cross-cut-test DIN EN ISO 2409 Gt 0 ■ Mandrel bending test cylindrical DIN EN ISO 1519 8 mm ■ Buchholz penetration test DIN EN ISO 2815 1,0 mm ■ Pencil Hardness acc. Wolff-Wilborn ISO 15184 3 H	
Resistance Test	■ on steel, purified alkaline ■ Condensate constant climate DIN EN ISO 6270-2 (CH) 504 hours water ingress Wb < 1 mm DIN EN ISO 4628-8	
Processing and application Dependent on plant and buildings	■ Pretreatment The substrate must be free of adhesion-impairing substances such as oil, grease, rust, scale, rolling skin, wax and separating agent residue. ■ Gloss value DIN EN ISO 2813 35-50 geometry 60° ■ pH-Value 8,2-8,5 ■ Cunductance 1800-2000 µS/cm ■ Solid Mass DIN EN ISO 3251 12-13,5 % ■ MEQ-Base-Value DIN EN ISO 15880 55-60 mg/g ■ Organic Solvent Content 0,5-1 % ■ Bath Temperature 24-27 °C	

Our technical data sheets are to provide you with advice based on our latest state of knowledge. This guidance does not release you from your own obligation to test our products for their suitability for your intended purposes and applications. The sale of our products is in accordance with our terms of business and delivery.



FREIOTHERM-ATL-Special

WA4900HRU905

	■ Coating Time	60-180 seconds
	■ Deposition Voltage	160-290 voltage
	■ Health & Safety at Work guidelines	The standard personal safety precautions must be observed when handling painting materials. Detailed information about dangerous goods, safety data and recommendations concerning Health & Safety at Work and environmental protection can be found in the corresponding safety data sheet.
Curing	■ Object temperature	Recommended baking temperature 20 Min./170 °C green cross-hatching = baking conditions with good final properties
		
Resistance to storage	■ One Turn-Over per year	Approx. 12 month in original packagings at an ambient temperature of 5 to 25 °C. Protect from frost. Open packages are to be used within a short time. The minimum storage stability of each batch is stated on the product label. The material does not necessarily become unusable if stored for longer than this period. However, for quality assurance purposes, an inspection of these materials is essential to ensure that they are still suitable for the intended application.
Specific comments	■ Test conditions	All information is based on a standard climate 23/50 DIN EN 23270. All information is based on our product knowledge an experience. We have no direct influence on the application itself. Please do not hesitate to contact us for further information. The information provided here contains reference values and does not constitute a specification.