



FREOCRYL-Powder Coating

PY1505B

Characteristics	■ Powder coating for decorative use on exteriors ■ Application, e.g. in the vehicle construction sector ■ high glossy, smooth ■ Good mechanical resistance and surface hardness ■ Very smooth to apply ■ Good light and weather resistance												
System Coating	■ System Liquid Coating For various applications, there are coatings available, whose optical appearance regarding colour, gloss degree and surface is in optimum balance.												
Technical / Physical Data	<table> <tr> <td>■ Binder-Base</td><td>GMA acrylic</td></tr> <tr> <td>■ Colour</td><td>colourless (= RA999)</td></tr> <tr> <td>■ Gloss value visual</td><td>high glossy</td></tr> <tr> <td>■ Test layer thickness</td><td>60 µm by colour RA999</td></tr> <tr> <td>■ Density calculated</td><td>1,15-1,2 g/cm³</td></tr> <tr> <td>■ Material usage</td><td>0,07 kg/m² with 60 µm mean test layer thickness</td></tr> </table>	■ Binder-Base	GMA acrylic	■ Colour	colourless (= RA999)	■ Gloss value visual	high glossy	■ Test layer thickness	60 µm by colour RA999	■ Density calculated	1,15-1,2 g/cm³	■ Material usage	0,07 kg/m² with 60 µm mean test layer thickness
■ Binder-Base	GMA acrylic												
■ Colour	colourless (= RA999)												
■ Gloss value visual	high glossy												
■ Test layer thickness	60 µm by colour RA999												
■ Density calculated	1,15-1,2 g/cm³												
■ Material usage	0,07 kg/m² with 60 µm mean test layer thickness												
Mechanical Test on steel panel ST 1405	<table> <tr> <td>■ Cross-cut-test DIN EN ISO 2409</td><td>Gt 0</td></tr> <tr> <td>■ Erichsen index DIN EN ISO 1520</td><td>>5 mm</td></tr> <tr> <td>■ Impact-Test DIN EN ISO 6272-1</td><td>>40 kg cm (front)</td></tr> </table>	■ Cross-cut-test DIN EN ISO 2409	Gt 0	■ Erichsen index DIN EN ISO 1520	>5 mm	■ Impact-Test DIN EN ISO 6272-1	>40 kg cm (front)						
■ Cross-cut-test DIN EN ISO 2409	Gt 0												
■ Erichsen index DIN EN ISO 1520	>5 mm												
■ Impact-Test DIN EN ISO 6272-1	>40 kg cm (front)												
Resistance Test	<table> <tr> <td>■ on chromatized aluminium</td><td></td></tr> <tr> <td>■ Condensate constant climate DIN EN ISO 6270-2 (CH)</td><td>240 hours Water ingress Wb < 1 mm DIN EN ISO 4628-8</td></tr> <tr> <td>■ Salt spray test (CASS) DIN EN ISO 9227</td><td>240 hours Water ingress Wb < 1 mm DIN EN ISO 4628-8</td></tr> <tr> <td>■ Chemical resistance</td><td>Needs to be checked. The temperature and concentration of chemicals have a major influence on the test outcome.</td></tr> </table>	■ on chromatized aluminium		■ Condensate constant climate DIN EN ISO 6270-2 (CH)	240 hours Water ingress Wb < 1 mm DIN EN ISO 4628-8	■ Salt spray test (CASS) DIN EN ISO 9227	240 hours Water ingress Wb < 1 mm DIN EN ISO 4628-8	■ Chemical resistance	Needs to be checked. The temperature and concentration of chemicals have a major influence on the test outcome.				
■ on chromatized aluminium													
■ Condensate constant climate DIN EN ISO 6270-2 (CH)	240 hours Water ingress Wb < 1 mm DIN EN ISO 4628-8												
■ Salt spray test (CASS) DIN EN ISO 9227	240 hours Water ingress Wb < 1 mm DIN EN ISO 4628-8												
■ Chemical resistance	Needs to be checked. The temperature and concentration of chemicals have a major influence on the test outcome.												
Processing and application Dependent on plant and buildings	■ Processing / Loading Corona ■ Pretreatment The substrate must be free of adhesion-impairing substances such as oil, grease, rust, scale, rolling skin, wax and separating agent residue. If requirements are more demanding than this, we recommend appropriate levels of phosphatizing or chromatizing. ■ Touch-up coating: on enquiry ■ Health & Safety at Work guidelines												

Our technical data sheets are to provide you with advice based on our latest state of knowledge. This guidance does not release you from your own obligation to test our products for their suitability for your intended purposes and applications. The sale of our products is in accordance with our terms of business and delivery.

Page: 1 / 2
Version: 0
16.05.2021

DIN EN ISO 9001
IATF 16949
EMAS

Emil Frei GmbH & Co. KG
Döggingen
Am Bahnhof 6
78199 Bräunlingen | GERMANY
Phone +49 [0] 7707.151-0
Fax +49 [0] 7707.151-238
www.freilacke.de
info@freilacke.de



FREOCRYL-Powder Coating PY1505B

Curing


The standard personal safety precautions must be observed when handling painting materials. Detailed information about dangerous goods, safety data and recommendations concerning Health & Safety at Work and environmental protection can be found in the corresponding safety data sheet.

■ Object temperature

Recommended baking temperature 20 min./170 °C

Baking window tested in colour shade RA999

green cross-hatching = baking conditions with good final properties



Resistance to storage

- Approx. 12 month in original packagings at an ambient temperature of 5 to 23 °C. Powder coatings must be stored in a cool and dry place.

The minimum storage stability of each batch is stated on the product label. The material does not necessarily become unusable if stored for longer than this period. However, for quality assurance purposes, an inspection of these materials is essential to ensure that they are still suitable for the intended application.

Specific comments

- **Protective screening:** 160 µm

- Not compatible with other powder coatings (crater formation).

■ Test conditions

All information is based on a standard climate 23/50 DIN EN 23270.

All information is based on our product knowledge and experience. We have no direct influence on the application itself. Please do not hesitate to contact us for further information.

The information provided here contains reference values and does not constitute a specification.