

Technical Data Sheet

DURELASTIC

Farbpaste BD7521XL1525

- Binder based on unsaturated polyester resin
- High amount of pigments
- High colouring power

	ingresisating power		
Technical / Physical data	Colour	traffic white	
	Original viscosity 30 to 40 sec. / 4 mm cup		. / 4 mm cup
	Density	2,0 g / ml + / - 0,1	
	calculated		
	Solid content	approx. 89 %	
	calculated		
Storability	Approx. 11 month in original packings at an ambient temperature of 15 to 25 °C, in case the original packings are tightly closed. Opened packing must be used very shortly. The minimum storage stability of each batch is mentioned on the product label. A storage time beyond the mentioned date doesn't necessarily mean that the material is unusable. In this case a check of the qualities which are important for the respective		
Processing and application	Application,	in original viscosity	
	Addition of	2 to 5 % 10 to 15 %	for colouring of resins for colouring of top coat resins
	Cleaning of working equipment EFD-Reinigungsmittel 400906		
	Advise for safety protection and protection of health The usual precautionery measures for ventilation as well as for personal protection are to be observed when handling painting materials. Detailled information about dangerous goods, sayfety data and recommendations concerning health protection and environment protection can be read in the corresponding safety data sheet.		
Special remarks	Test conditions		
	*Indication of the delivery viscosity according to DIN 53211:		
	DIN 53211 was withdrawn in October 1996.		

On request the value is available according to DIN EN ISO 2431.

All information is based on a standard climate 20/65 DIN 50014.

All information are based on our product knowledge and experience. To the application we have no direct influence. For further information please don't hesitate to contact us.

The information mentioned herein are reference values and are not given as specification.

25. Oktober 2007 / Version: 1

Our technical data sheets are to advise you according to our latest state of knowledge. This information does not release you from own tests of our products in view to the ability for the intended procedures and applications. The sale of our products is an accordance with our terms of business and delivery.

DIN EN ISO 9001 VDA 6.1 EMAS II Page 1 from 1

Emil Frei GmbH & Co. Lackfabrik Döggingen Am Bahnhof 6 D-78195 Bräunlingen Phone: +49 (0)7707 151-0 Fax: +49 (0)07707 151-

info@freilacke.de, www.freilacke.de