


FREIOTHERM-Hydro-Coating
WO1895G

Characteristics	<ul style="list-style-type: none"> ■ Water-thinnable baking coating ■ Application, e.g. in the mechanical engineering and plant construction sector ■ Good condensation resistance ■ Good hardness and elasticity 																						
Technical / Physical Data	<table border="1"> <tr> <td>■ Binder-Base</td> <td>Combination of polyester/amino resin</td> </tr> <tr> <td>■ Colour</td> <td>All common colour shades</td> </tr> <tr> <td>■ Gloss value DIN EN ISO 2813</td> <td>glossy 60-70 Angle 60°</td> </tr> <tr> <td>■ Viscosity DIN 53211 (formerly)</td> <td>Flow time 30-40 seconds 4 mm viscosity cup</td> </tr> <tr> <td>■ Thinner</td> <td>demineralised water</td> </tr> <tr> <td>■ pH-Value</td> <td>8,7-9,0</td> </tr> <tr> <td>■ Density calculated</td> <td>1,25-1,40 g/ml</td> </tr> <tr> <td>■ Solid Mass calculated</td> <td>50-55 %</td> </tr> <tr> <td>■ Solid content in volume calculated</td> <td>240-260 ml/kg</td> </tr> <tr> <td>■ Material usage theoretical, without application loss</td> <td>120-150 g/m², Layer thickness 40 µm</td> </tr> <tr> <td>■ Reference colour of the specified values</td> <td>Colour of WO1895GRA916</td> </tr> </table>	■ Binder-Base	Combination of polyester/amino resin	■ Colour	All common colour shades	■ Gloss value DIN EN ISO 2813	glossy 60-70 Angle 60°	■ Viscosity DIN 53211 (formerly)	Flow time 30-40 seconds 4 mm viscosity cup	■ Thinner	demineralised water	■ pH-Value	8,7-9,0	■ Density calculated	1,25-1,40 g/ml	■ Solid Mass calculated	50-55 %	■ Solid content in volume calculated	240-260 ml/kg	■ Material usage theoretical, without application loss	120-150 g/m ² , Layer thickness 40 µm	■ Reference colour of the specified values	Colour of WO1895GRA916
■ Binder-Base	Combination of polyester/amino resin																						
■ Colour	All common colour shades																						
■ Gloss value DIN EN ISO 2813	glossy 60-70 Angle 60°																						
■ Viscosity DIN 53211 (formerly)	Flow time 30-40 seconds 4 mm viscosity cup																						
■ Thinner	demineralised water																						
■ pH-Value	8,7-9,0																						
■ Density calculated	1,25-1,40 g/ml																						
■ Solid Mass calculated	50-55 %																						
■ Solid content in volume calculated	240-260 ml/kg																						
■ Material usage theoretical, without application loss	120-150 g/m ² , Layer thickness 40 µm																						
■ Reference colour of the specified values	Colour of WO1895GRA916																						
Substrate	<ul style="list-style-type: none"> ■ Steel ■ Steel - preliminary test required for galvanised substrates ■ Steel, passivated or pretreated substrates 																						
Pretreatment	<ul style="list-style-type: none"> ■ The substrate must be free of adhesion-impairing substances such as oil, grease, wax and separating agent residue. Preliminary tests are recommended for assuring the suitability of coating qualities on the substrate. 																						
Structure recommendation	<table border="1"> <tr> <td>■ Substrate</td> <td>on iron-phosphated steel plate</td> </tr> <tr> <td>■ Top coat</td> <td>WO1895GRA916 Dry film thickness 30 µm</td> </tr> </table>	■ Substrate	on iron-phosphated steel plate	■ Top coat	WO1895GRA916 Dry film thickness 30 µm																		
■ Substrate	on iron-phosphated steel plate																						
■ Top coat	WO1895GRA916 Dry film thickness 30 µm																						
Mechanical Test	<table border="1"> <tr> <td>■ Cross-cut-test DIN EN ISO 2409</td> <td>Gt 0</td> </tr> <tr> <td>■ Chemical resistance</td> <td>Needs to be checked. The temperature and concentration of chemicals have a major influence on the test outcome.</td> </tr> </table>	■ Cross-cut-test DIN EN ISO 2409	Gt 0	■ Chemical resistance	Needs to be checked. The temperature and concentration of chemicals have a major influence on the test outcome.																		
■ Cross-cut-test DIN EN ISO 2409	Gt 0																						
■ Chemical resistance	Needs to be checked. The temperature and concentration of chemicals have a major influence on the test outcome.																						
Processing and application	<ul style="list-style-type: none"> ■ Prior to use, stir well or mix components homogeneously (e.g. with fast mixer). To prevent skin formation, over-coat with water. <p>Dry film thickness must not exceed 40 µm - risk of reaction bubbles.</p>																						

Our technical data sheets are to provide you with advice based on our latest state of knowledge. This guidance does not release you from your own obligation to test our products for their suitability for your intended purposes and applications. The sale of our products is in accordance with our terms of business and delivery.



FREIOTHERM-Hydro-Coating
WO1895G


■ Object temperature	10-30 °C
■ Processing conditions	Room temperature 18-25 °C Relative humidity 40-60 %
■ High pressure spraying	as delivered viscosity Nozzle: 1,4 mm Spray pressure 3-4 bar
■ Electrostatic	possible, system-specific
■ Cleaning of equipment	Immediately with water - possibly with addition of 5-10 % by weight EFD cleaning agent 400916. Dried-on equipment with org. solvents, e.g. EFD thinner 400424.
■ Health & Safety at Work guidelines	The standard personal safety precautions must be observed when handling painting materials. Detailed information about dangerous substances, safety data and recommendations concerning Health & Safety at Work and environmental protection can be found in the corresponding safety data sheet.

Curing	■ Oven drying	15 min./ 140 °C - 10 min./ 150 °C
	■ Object temperature	green cross-hatching = baking conditions with good final properties

Resistance to storage	<p>■ Approx. 12 month in original packagings at an ambient temperature of 5 to 25 °C. Protect from frost. Open packages are to be used within a short time.</p> <p>The minimum storage stability of each batch is stated on the product label. The material does not necessarily become unusable if stored for longer than this period. However, for quality assurance purposes, an inspection of these materials is essential to ensure that they are still suitable for the intended application.</p>
------------------------------	---

Specific comments	<p>■ EFD-info Refer to the EFD information for further technical information. Nr. 111</p> <p>■ Test conditions</p>
--------------------------	--

Our technical data sheets are to provide you with advice based on our latest state of knowledge. This guidance does not release you from your own obligation to test our products for their suitability for your intended purposes and applications. The sale of our products is in accordance with our terms of business and delivery.



FREIOTHERM-Hydro-Coating **WO1895G**

All information is based on a standard climate 23/50 DIN EN 23270.

All information is based on our product knowledge and experience. We have no direct influence on the application itself. Please do not hesitate to contact us for further information.

The information provided here contains reference values and does not constitute a specification.