



# FREIOTHERM-AT-Color Concentrat

## 370530

<b>Characteristics</b>	<ul style="list-style-type: none"> <li>■ Tinting Paste</li> </ul>										
<b>Technical / Physical Data</b>	<table> <tr> <td>■ Binder-Base</td><td>Acrylic Resin</td></tr> <tr> <td>■ Colour</td><td>orange Based on the specified colour template (i.e. RAL)</td></tr> <tr> <td>■ Solid Mass DIN EN ISO 3251</td><td>38-42 %</td></tr> <tr> <td>■ Density calculated</td><td>1,10 g/cm<sup>3</sup></td></tr> <tr> <td>■ MEQ-Base-Value DIN EN ISO 15880</td><td>20-30</td></tr> </table>	■ Binder-Base	Acrylic Resin	■ Colour	orange Based on the specified colour template (i.e. RAL)	■ Solid Mass DIN EN ISO 3251	38-42 %	■ Density calculated	1,10 g/cm <sup>3</sup>	■ MEQ-Base-Value DIN EN ISO 15880	20-30
■ Binder-Base	Acrylic Resin										
■ Colour	orange Based on the specified colour template (i.e. RAL)										
■ Solid Mass DIN EN ISO 3251	38-42 %										
■ Density calculated	1,10 g/cm <sup>3</sup>										
■ MEQ-Base-Value DIN EN ISO 15880	20-30										
<b>Processing and application</b> Dependent on plant and buildings	<ul style="list-style-type: none"> <li>■ Method           <p>Direct addition to the basin is not possible ! For a good mix, add to the overflow/weir or mixing tube ! The procedure is dependant upon various factors and is therefore matched to the application technology to the individual plant.</p> </li> <li>■ <b>Health &amp; Safety at Work guidelines</b> <p>The standard personal safety precautions must be observed when handling painting materials. Detailed information about dangerous goods, safety data and recommendations concerning Health &amp; Safety at Work and environmental protection can be found in the corresponding safety data sheet.</p> </li> </ul>										
<b>Resistance to storage</b>	<ul style="list-style-type: none"> <li>■ Approx. 6 Monate month in original packagings at an ambient temperature of 5 to 25 °C. Protect from frost. Open packages are to be used within a short time.</li> </ul> <p>The minimum storage stability of each batch is stated on the product label. The material does not necessarily become unusable if stored for longer than this period. However, for quality assurance purposes, an inspection of these materials is essential to ensure that they are still suitable for the intended application.</p>										
<b>Specific comments</b>	<ul style="list-style-type: none"> <li>■ <b>Test conditions</b> <p>All information is based on a standard climate 23/50 DIN EN 23270. All information is based on our product knowledge and experience. We have no direct influence on the application itself. Please do not hesitate to contact us for further information. The information provided here contains reference values and does not constitute a specification.</p> </li> </ul>										