




# FREIOTHERM-Hydro-Primer WO1870H

<b>Characteristics</b>	<ul style="list-style-type: none"> <li>Water-thinnable baking coating</li> <li>Application, e.g. in the automotive sector</li> <li>Good stone chip resistance</li> <li>Can be coated over with powder coatings</li> </ul>																						
<b>Technical / Physical Data</b>	<table> <tr> <td>Binder-Base</td><td>Combination of acrylate/polyester/amino resin</td></tr> <tr> <td>Colour</td><td>All common colour shades</td></tr> <tr> <td>Gloss value visual</td><td>satin mat</td></tr> <tr> <td>Viscosity DIN 53211 (formerly)</td><td>Flow time 30-40 seconds 4 mm viscosity cup</td></tr> <tr> <td>Thinner</td><td>demineralised water</td></tr> <tr> <td>pH-Value</td><td>8,0-9,0</td></tr> <tr> <td>Density calculated</td><td>1,18-1,20 g/ml</td></tr> <tr> <td>Solid Mass calculated</td><td>37-43 %</td></tr> <tr> <td>Solid content in volume calculated</td><td>220-240 ml/kg</td></tr> <tr> <td>Material usage theoretical, without application loss</td><td>80-90 g/m², Layer thickness 20 µm</td></tr> <tr> <td>Reference colour of the specified values</td><td>Colour of WO1870HRU740</td></tr> </table>	Binder-Base	Combination of acrylate/polyester/amino resin	Colour	All common colour shades	Gloss value visual	satin mat	Viscosity DIN 53211 (formerly)	Flow time 30-40 seconds 4 mm viscosity cup	Thinner	demineralised water	pH-Value	8,0-9,0	Density calculated	1,18-1,20 g/ml	Solid Mass calculated	37-43 %	Solid content in volume calculated	220-240 ml/kg	Material usage theoretical, without application loss	80-90 g/m², Layer thickness 20 µm	Reference colour of the specified values	Colour of WO1870HRU740
Binder-Base	Combination of acrylate/polyester/amino resin																						
Colour	All common colour shades																						
Gloss value visual	satin mat																						
Viscosity DIN 53211 (formerly)	Flow time 30-40 seconds 4 mm viscosity cup																						
Thinner	demineralised water																						
pH-Value	8,0-9,0																						
Density calculated	1,18-1,20 g/ml																						
Solid Mass calculated	37-43 %																						
Solid content in volume calculated	220-240 ml/kg																						
Material usage theoretical, without application loss	80-90 g/m², Layer thickness 20 µm																						
Reference colour of the specified values	Colour of WO1870HRU740																						
<b>Substrate</b>	Aluminium																						
<b>Pretreatment</b>	The substrate must be free of adhesion-impairing substances such as oil, grease, rust, scale, rolling skin, wax and separating agent residue. Preliminary tests are recommended for assuring the suitability of coating qualities on the substrate. Chromating or corresponding chrome-free conversion coatings.																						
<b>Structure recommendation</b>	<table> <tr> <td>Substrate</td><td>Aluminium</td></tr> <tr> <td>Primer</td><td>WO1870H Dry film thickness 20 µm</td></tr> <tr> <td>Base coat</td><td>WO1869H Dry film thickness 20 µm</td></tr> <tr> <td>Clear coat</td><td>PY1005BRA999 Dry film thickness 90 µm</td></tr> </table>	Substrate	Aluminium	Primer	WO1870H Dry film thickness 20 µm	Base coat	WO1869H Dry film thickness 20 µm	Clear coat	PY1005BRA999 Dry film thickness 90 µm														
Substrate	Aluminium																						
Primer	WO1870H Dry film thickness 20 µm																						
Base coat	WO1869H Dry film thickness 20 µm																						
Clear coat	PY1005BRA999 Dry film thickness 90 µm																						
<b>Mechanical Test</b>	<table> <tr> <td>Cross-cut-test DIN EN ISO 2409</td><td>Gt 0</td></tr> <tr> <td>Stone chipping test DIN EN ISO 20567-1</td><td>Characteristic value &lt;2</td></tr> </table>	Cross-cut-test DIN EN ISO 2409	Gt 0	Stone chipping test DIN EN ISO 20567-1	Characteristic value <2																		
Cross-cut-test DIN EN ISO 2409	Gt 0																						
Stone chipping test DIN EN ISO 20567-1	Characteristic value <2																						
<b>Processing and application</b>	<ul style="list-style-type: none"> <li>Prior to use, stir well or mix components homogeneously (e.g. with fast mixer). To prevent skin formation, over-coat with water.</li> <li>Object temperature 15-35 °C</li> </ul>																						

Our technical data sheets are to provide you with advice based on our latest state of knowledge. This guidance does not release you from your own obligation to test our products for their suitability for your intended purposes and applications. The sale of our products is in accordance with our terms of business and delivery.



# FREIOTHERM-Hydro-Primer

## WO1870H

	■ Processing conditions	Room temperature 15-25 °C Relative humidity 50-70 %
	■ Electrostatic	possible, system-specific
	■ ESTA high rotation	as delivered viscosity
	■ Cleaning of equipment	Immediately with water - possibly with addition of 5-10 % by weight EFD cleaning agent 400916. Dried-on equipment with org. solvents, e.g. EFD thinner 400424.
	■ <b>Health &amp; Safety at Work guidelines</b>	The standard personal safety precautions must be observed when handling painting materials. Detailed information about dangerous substances, safety data and recommendations concerning Health & Safety at Work and environmental protection can be found in the corresponding safety data sheet.
<b>Curing</b>	■ Intermediate drying	10 min./ 120 °C
	■ Oven drying	10 min./ 180 °C - 20 min./ 160 °C
	■ <b>Object temperature</b>	Baking window on request
<b>Resistance to storage</b>	■	Approx. 12 month in original packagings at an ambient temperature of 5 to 25 °C. Protect from frost. Open packages are to be used within a short time.
		The minimum storage stability of each batch is stated on the product label. The material does not necessarily become unusable if stored for longer than this period. However, for quality assurance purposes, an inspection of these materials is essential to ensure that they are still suitable for the intended application.
<b>Specific comments</b>	■ <b>Test conditions</b>	All information is based on a standard climate 23/50 DIN EN 23270. All information is based on our product knowledge and experience. We have no direct influence on the application itself. Please do not hesitate to contact us for further information.
		The information provided here contains reference values and does not constitute a specification.