

FREOPOX-Powder Coating PB4902A


Characteristics	■ Powder coating for interior use ■ Application, e.g. in the functional furniture and storage technology sector ■ satin mat, smooth ■ Good mechanical resistance and surface hardness ■ Cost-effective basic quality												
System Coating	■ System Liquid Coating For various applications, there are coatings available, whose optical appearance regarding colour, gloss degree and surface is in optimum balance.												
Technical / Physical Data	<table> <tr> <td>■ Binder-Base</td><td>epoxy polyester resin</td></tr> <tr> <td>■ Colour</td><td>all common colour shades</td></tr> <tr> <td>■ Gloss value DIN EN ISO 2813</td><td>satin mat 40-60 geometry 60°</td></tr> <tr> <td>■ Test layer thickness</td><td>70 µm by colour RAL 7035</td></tr> <tr> <td>■ Density calculated</td><td>1,2-1,7 g/cm³ colour-dependent</td></tr> <tr> <td>■ Material usage</td><td>0,1 kg/m² with 70 µm mean test layer thickness</td></tr> </table>	■ Binder-Base	epoxy polyester resin	■ Colour	all common colour shades	■ Gloss value DIN EN ISO 2813	satin mat 40-60 geometry 60°	■ Test layer thickness	70 µm by colour RAL 7035	■ Density calculated	1,2-1,7 g/cm³ colour-dependent	■ Material usage	0,1 kg/m² with 70 µm mean test layer thickness
■ Binder-Base	epoxy polyester resin												
■ Colour	all common colour shades												
■ Gloss value DIN EN ISO 2813	satin mat 40-60 geometry 60°												
■ Test layer thickness	70 µm by colour RAL 7035												
■ Density calculated	1,2-1,7 g/cm³ colour-dependent												
■ Material usage	0,1 kg/m² with 70 µm mean test layer thickness												
Mechanical Test on steel panel ST 1405	<table> <tr> <td>■ Cross-cut-test DIN EN ISO 2409</td><td>Gt 0</td></tr> <tr> <td>■ Erichsen index DIN EN ISO 1520</td><td>>2 mm</td></tr> <tr> <td>■ Impact-Test DIN EN ISO 6272-1</td><td>>40 kg cm (front)</td></tr> </table>	■ Cross-cut-test DIN EN ISO 2409	Gt 0	■ Erichsen index DIN EN ISO 1520	>2 mm	■ Impact-Test DIN EN ISO 6272-1	>40 kg cm (front)						
■ Cross-cut-test DIN EN ISO 2409	Gt 0												
■ Erichsen index DIN EN ISO 1520	>2 mm												
■ Impact-Test DIN EN ISO 6272-1	>40 kg cm (front)												
Resistance Test	■ on iron-phosphatized steel sheet ■ Condensate constant climate DIN EN ISO 6270-2 (CH) 240 hours Water ingress Wb < 1 mm DIN EN ISO 4628-8 ■ Salt spray test (NSS) DIN EN ISO 9227 120 hours Water ingress Wb < 1 mm DIN EN ISO 4628-8 ■ Chemical resistance Needs to be checked. The temperature and concentration of chemicals have a major influence on the test outcome.												
Processing and application Dependent on plant and buildings	■ Processing / Loading Corona, Tribo ■ Pretreatment The substrate must be free of adhesion-improving substances such as oil, grease, rust, scale, rolling skin, wax and separating agent residue. If requirements are more demanding than this, we recommend appropriate levels of phosphatizing or chromating. ■ Touch-up coating: on enquiry ■ Health & Safety at Work guidelines The standard personal safety precautions must be observed when handling painting												

Our technical data sheets are to provide you with advice based on our latest state of knowledge. This guidance does not release you from your own obligation to test our products for their suitability for your intended purposes and applications. The sale of our products is in accordance with our terms of business and delivery.


Page: 1 / 2
Version: 0
16.05.2021

DIN EN ISO 9001
IATF 16949
EMAS

Emil Frei GmbH & Co. KG
Döggingen
Am Bahnhof 6
78199 Bräunlingen | GERMANY
Phone +49 [0] 7707.151-0
Fax +49 [0] 7707.151-238
www.freilacke.de
info@freilacke.de



FREOPOX-Powder Coating PB4902A

	materials. Detailed information about dangerous goods, safety data and recommendations concerning Health & Safety at Work and environmental protection can be found in the corresponding safety data sheet.
Curing	Object temperature Recommended baking temperature 10 min./180 °C Baking window tested in colour shade RAL 7035 green cross-hatching = baking conditions with good final properties 
Resistance to storage	Approx. 36 month in original packagings at an ambient temperature of 5 to 25 °C. Powder coatings must be stored in a cool and dry place. The minimum storage stability of each batch is stated on the product label. The material does not necessarily become unusable if stored for longer than this period. However, for quality assurance purposes, an inspection of these materials is essential to ensure that they are still suitable for the intended application.
Specific comments	Protective screening: 160 µm Compatibility with other powder coatings: Needs to be checked Test conditions All information is based on a standard climate 23/50 DIN EN 23270. All information is based on our product knowledge an experience. We have no direct influence on the application itself. Please do not hesitate to contact us for further information. The information provided here contains reference values and does not constitute a specification.